

T E S T C E R T I F I C A T E

Product: TREATEX Hardwax Oil Traditional
(application according to producer instructions)

Order: Determination of the slippery resistance

Test methods: - Determination of the slippery resistance according to E DIN 51131
- Determination of the slippery resistance according to EN 13893

Test report: 276078

Test result:

Slippery resistance according to E DIN 51131 (Leather slider)		Slippery resistance according to EN 13893 (Rubber- and leather slider)
Sliding friction coefficient μ	Assessment of the slippery resistance (*)	Sliding friction coefficient μ
0,42	conditional safe	0,58

(*) $\mu < 0,30$ = unsafe

$0,30 \leq \mu \leq 0,45$ = conditional safe

$\mu > 0,45$ = safe

Classification in levels of use according to the „ihd Anforderungsprofil für Holzfußbodenlackierungen“, Version 01/2003

Requirements of level of use 1 – 6 are fulfilled**

(**) Level of use 1 = moderate use in the domestic area
Level of use 6 = heavy / intensive use in the commercial area

Dresden, 21.03.2006



Head of laboratory




Engineer in charge